

**KR9608119B1:**

## **POLYPROPYLENE RESIN COMPOSITION**

The resin composition comprises polyester resin and wood powder, suitable for molding fabrications such as injection molding or extrusion molding, the composition is prepared by the steps of: (A) per 100 parts by weight of wood powder surface-treated with a isocyanate system compound, mixing 15 to 70 parts by weight of denatured-polyolefin resin having a softening temperature of lower than 115 deg. C. with the wood powder at a temperature ranging from that of the above softening temperature of denatured-polypropylene resin to that of 120 deg. C.; (B) mixing and melting resultant compound with polypropylene resin.